

N-650 Technical Specification



Himadri

Product Description

- It is a same surface area (compared to N660) and high structure general purpose high modulus black. Compared to N-550, it gives even lower heat build-up, long fatigue life and better processibility. It is used for body compounds in passenger tires, including innerliners, as well as numerous rubber goods e.g., injection moulding.

Technical Specifications

	Test Method	Units	Spec.
Iodine Adsorption No.	D-1510	(g/kg)	36.0±5.0
Nitrogen Surface Area	D-6556	(m ² /g)	36.0±5.0
STSA	D-6556	m ² /g)	35.0±5.0
Oil Absorption No.	D-2414	(cc/100 g)	122.0±5.0
COAN	D-3493	(cc/100g)	84.0±5.0
Heating Loss	D-1509	%	1.5 max.(Big Bag) 2.5 max (Paper Bag)
Sieve Residue @ 325 mesh	D-1514	%	0.050 max.
Sieve Residue @ 35 mesh	D-1514	%	0.001 max.
Ash Content	D-1506	%	1.0 max.
Pellet Hardness (Avg. of 20)	D-5230	gf	50.0 max.
Individual Max. Pellet Hardness	D-5230	gf	90.0 max.
Fines Content	D-1508	%	8.0 max.(Big Bag) 12.0 max (Paper Bag)
pH	D-1512	-	6 to 9
Pour Density	D-1513	Kg/m ³	370±25
Toluene Discoloration	D-1618	%	80.0 min.

Packaging

- 25 kgs paper bag and 500 to 1200 kgs big bag

Disclaimer

This information is provided as a convenience and for informational purposes only. No guarantee or warranty as to this information, or any product to which it relates, is given or implied. This information may contain inaccuracies, errors or omissions and Himadri Speciality Chemical Ltd. disclaims all warranties express or implied, including merchantability or fitness for a particular purpose as to (i) such information, (ii) any product or (iii) intellectual property infringement. In no event is Himadri Speciality Chemical Ltd. responsible for, and does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.