

## Product Technical Data Sheet



**Product Name:** N660  
**Revision date:** 2016-8-30  
**Version:** 1.0

### N660: General Purpose Furnace black

#### Product Description

Impart low modulus and low tensile as per ASTM NR compound compared to N550 with equivalent hardness.

#### Product Features

- Medium Structure Black
- Low Surface Area
- Sieve Residue less than 200 ppm in 325 Mesh
- Low reinforcing black

#### Applications

- Carcass compound/ Tube/ beads/ plies/ cycle tyre/ tube/ V belt
- Hose application. Engine mounts and belt inner liner/ Door seal/ cable/ oil seals/ conveyor belts

#### Technical Specifications

	Test Method	Units	Specified range
<b>Tint</b>	<b>D-3265</b>	% ( ITRB #3)	58 ± 5
<b>DBP No. (OAN)</b>	<b>D-2414</b>	(cc/100 g)	90 ± 5
<b>24 M<sub>4</sub> DBP NO. (COAN)</b>	<b>D-3493</b>	(cc/100g)	72 - 75
<b>CTAB</b>	<b>D-3765</b>	(m <sup>2</sup> / g)	35 ± 5
<b>STSA</b>	<b>D-6556</b>	m <sup>2</sup> / g	34 - 35
<b>N<sub>2</sub> SA</b>	<b>D-6556</b>	(m <sup>2</sup> / g)	34 - 36
<b>I<sub>2</sub> No.</b>	<b>D-1510</b>	(mg/g)	36 ± 5
<b>pH</b>	<b>D-1512</b>		7.5 ± 1.5
<b>Ash (max.)</b>	<b>D-1506</b>	% (max.)	0.5
<b>P.D.</b>	<b>D-1513</b>	kg/m <sup>3</sup> )	432 - 458

## Product Technical Data Sheet



**Product Name:** N660  
**Revision date:** 2016-8-30  
**Version:** 1.0

<b>S.R # 325 (max.)</b>	<b>D-1514</b>	%	0.03
<b>S.R. # 100 (max.)</b>	<b>D-1514</b>	%	0.003
<b>S.R. # 35 (max.)</b>	<b>D-1514</b>	%	0.0005
<b>M 300% (Diff. from IRB#8) 30' @ 145 ° C</b>	<b>D-3192/ D-412</b>	(Mpa)	-2.39 ± 1.0
<b>Fines 5' (Max)</b>	<b>D-1508</b>	%	7.0
<b>Pellet Hardness</b>	<b>D-5230</b>	(gf)	15 - 50
<b>Heating Loss (Max.)</b>	<b>D-1509</b>	%,	1.5 (PB) / 1.0 (JB)
<b>T.D. (Min.)</b>	<b>D-1618</b>	% T	80
<b>Mass Strength</b>	<b>D-1937</b>	kgf	22 ± 5

### Packaging

- May be available in 25 kg two ply craft paper bag
- 1000 kg jumbo bags
- 1200 kg jumbo bags

### Disclaimer

This information is provided as a convenience and for informational purposes only. No guarantee or warranty as to this information, or any product to which it relates, is given or implied. This information may contain inaccuracies, errors or omissions and Himadri Speciality Chemical Ltd. disclaims all warranties express or implied, including merchantability or fitness for a particular purpose as to (i) such information, (ii) any product or (iii) intellectual property infringement. In no event is Himadri Speciality Chemical Ltd. responsible for, and does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.