



DUTRAL[®]

EP(D)M

TER 7040

Ethylene - Propylene - Diene Terpolymer

Dutral[®] TER 7040 is an Ethylene - Propylene - Diene polymer produced by suspension polymerisation using an improved Ziegler-Natta Catalyst at the Ferrara production facility in Italy. A non-staining antioxidant is added during the production process.

Main Properties	Unit	Value
Mooney Viscosity ML 1+4(125 °C)	MU	87
Volatiles content	% wt	0.5 max
Ash content	% wt	0.3 max
Propylene content	% wt	40
ENB content	% wt	6,5

Key Features

Dutral[®] elastomers are characterized by excellent resistance to ageing and weathering, good resistance to both high and low temperatures, low permanent set values, good resistance to a large number of chemicals. Dutral[®] TER 7040 is a high molecular weight terpolymer of medium-high diene content. It is characterized by high loading capacity, easier dispersion of ingredients during mixing, good dimensional stability and low temperature elasticity; the medium-high ENB content ensure a fast curing. Dutral[®] TER 7040 can be advantageously used in extrusion applications mainly where high mechanical properties and low temperature performances are required

Main Applications

Building, automotive compact profiles, mechanical goods

Physical Form

Bales wrapped with low melting point polyethylene film; typical bale weight: 25 kg.

Packaging

Cardboard box of 750 kg containing 30 bales (1050 x 1250 x h1050 mm).

Storage Conditions

Store in dry and vented areas, avoiding temperatures above 35 °C and direct sunlight. It is recommended that temperatures above 30 °C be avoided for prolonged storage times in order to not deteriorate the quality of the product and reduce its shelf life. Shelf life : 36 months.

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor liability accepted with respect to the use of such information and data.