

EVA

E265F

EVA for bridge firing

Application

Foam, Crosslinked foam, Athletic shoe in-sole/mid-sole

Characteristics

Good processability and crosslinking property during foaming process, Good mechanical properties, Uniform additive dispersibility

Physical properties

Item	Test Method	Unit	Typical Value
Melt index	ASTM D1238 (190°C, 2.16kg)	g/10min	6
Density	ASTM D1505	g/cm ³	0.947
VA content	HTC Method	%	26
Melt temperature	HTC Method	°C	73
Tensile strength(at break)	ASTM D638	kg/cm ²	180
Elongation (at break)	ASTM D638	%	800
Shore hardness	ASTM D2240	D Scale	28
Vicat softening point	ASTM D1525	°C	47
Brittleness temperature	ASTM D746	°C	<-70

Note) Data shown above are representative values for reference purposes only, and not to be construed as specifications.

Certification

Hanwha TotalEnergies Petrochemical are limitations in applying Hanwha TotalEnergies E265F for food packaging purposes.

For further inquiries, please contact Customer Technical Service.

Contact information

Hanwha TotalEnergies Petrochemical co. Ltd.

Disclaimer

This document is copyrighted by Hanwha TotalEnergies Petrochemical. All information is for reference only and is not the specifications of the final product. Customers should make their own judgments as to whether our products and information serve a particular purpose and what regulations apply to customers' use of such products. Hanwha TotalEnergies Petrochemical is not responsible or obligated for the contents of this document. Hanwha TotalEnergies Petrochemical provides no warranties of any kind, either express or implied (such as merchantability and or fitness for a particular purpose, etc.) with respect to any information contained in this material. Hanwha TotalEnergies Petrochemical may arbitrarily change the contents of this material without prior notice.