1. Introduction

HANWHA P-1000F is a PVC homopolymer made by suspension polymerization. P-1000F has established a deserved reputation for low fish-eye count and excellent plasticizer absorption. It is recommended for high-quality product manufacturing such as automotive parts, gasket, cable sheath, clean wrap, deco sheet, film.

2. Applications

Automotive interior & exterior profile, cable sheath, gasket, wrap, sheet & film

3. Properties

Properties	Methods	Unit	Typical value
Degree of polymerization	JIS K6720-2	-	1000±50
K-Value	DIN 53726	-	66
Apparent bulk density	ASTM D1895	g/㎤	0.52±0.04
Volatility	ASTM D3030	%	Below 0.30
Sieve analysis (42mesh pass)	HCC method	%	100

*The values given above are typical test results which should be used as a guide only. They do not form the whole or part of a specification or guarantee.

4. Storage, Packaging, Safety

Storage

P-1000F should be stored dry conditions and at room temperature below 25℃.

Safety and Handling

The Hanwha Chemical Corporation provides its customers with a product specific Material Safety Data Sheet (MSDS) to cover potential health effects, safe handling, use and transportation. Hanwha Chemical Corporation strongly encourage its customers to review MSDS on its products and other materials prior to their use. P-1000F is normally supplied as a power in 25kg polypropylene inner coated paper bag, 500kg flecon bag as well as in bulk form. P-1000F is not formulated to contain any hazardous or regulated materials such as lead, cadmium, mercury, and chromium compounds. And Hanwha Chemical

The information given herein and other otherwise supplied to users is based on our general experience and where applicable, on the results of tests on samples of typical manufacture. However, because of the many factors which are outside knowledge and control, which can effect the use of these products, users must rely on their own judgment and we cannot accept liability for any injury, loss or damage resulting from reliance upon such information.

Corporation guarantee that P-1000F do not include any hazardous or regulated materials during the manufacturing process.

General Information

The data and recommendations contained in this brochure represent the current state of our knowledge and serve as a guide only to our products and their potential applications. Therefore, no warranty of specific properties of the products mentioned herein nor of their suitability or fitness for a particular purpose is implied.

Further information and recommendations for processing can be obtained from our technical support staff and representatives.

RAJSHILA®

The information given herein and other otherwise supplied to users is based on our general experience and where applicable, on the results of tests on samples of typical manufacture. However, because of the many factors which are outside knowledge and control, which can effect the use of these products, users must rely on their own judgment and we cannot accept liability for any injury, loss or damage resulting from reliance upon such information.