

General Silicone Rubber For Extrusion

High transparency, and processability for extrusion. Suitable for DCBP Sulfide and making various kinds of extrusion rubber hose, strip and wire.

Grade	Apperance	Hardness(Shore A)	Tensile Strength (Mpa) ≥	Tear Strength (kN/m) ≥	Elongation(%) ≥	Tensile Set (%) ≤	Rebound (%) ≥
HS-1131	Translucent	27-33	5				
HS-1141	Translucent	37-43	7	13	550	8	60
HS-1151	Translucent	37-53	7	16	400	8	50
HS-1161	Translucent	57-63	7	18	320	8	50
HS-1171	Translucent	67-73	6.5	18	280	8	45
HS-1181	Translucent	77-83	6	16	200	8	40
				16	150	8	40

RAJSHILA®