

Standard Silicone Rubber for Extrusion

High transparency and processability for extrusion. Suitable for the high transparency extrusion products with DCBP or platinum vulcanization.

Grade	Apperance	Hardness(Shore A)	Tensile Strength (Mpa) ≥	Tear Strength (kN/m) ≥	Elongation(%) ≥	Tensile Set (%) ≤	Rebound (%) ≥
HS-1131PT	Translucent	31±2	6	14	550	8	60
HS-1141PT	Translucent	39-43	8	18	600	6	60
HS-1151PT	Translucent	48-52	8	18	450	6	55
HS-1161PT	Translucent	58-62	8	20	350	6	50
HS-1171PT	Translucent	68-72	8	20	270	6	45
HS-1181PT	Translucent	78-82	7.5	20	200	4	45

RAJSHILA®