

Common Silicone Rubber For Molding

Good transparency, rebound resilience and demoulding performance. Suitable for swimming cap, various kinds of keypads, home appliances, cake molds and seals.

Grade	Apperance	Hardness(Shore A)	Tensile Strength (Mpa) ≥	Tear Strength (kN/m) ≥	Elongation(%) ≥	Tensile Set (%) ≤	Rebound (%) ≥
HS-2111	Translucent	10-15	3	9	800	10	56
HS-2121	Translucent	17-23	3	8	600	10	55
HS-2131	Translucent	27-33	5	13	550	8	60
HS-2141	Translucent	37-43	6.5	16	450	8	60
HS-2151	Translucent	47-53	6	17	350	8	55
HS-2161	Translucent	57-63	6	17	300	7	50
HS-2171	Translucent	67-73	6	16	200	7	43
HS-2181	Translucent	77-83	6	14	150	8	40

RAJSHILA®