## Standard Silicone Rubber

High glossiness with good rebound resilience, economic and demoulding performance. Suitable for high appearance required molding products.

| Grade | Apperance | Hardness(Shore A) | Tensile Strength (Mpa) ≥ | Tear Strength (kN/m) ≥ | Elongation(%) ≥ | Tensile Set (%) ≤ | Rebound (%) ≥ |
|---|---|---|---|---|---|---|---|
| HS -3430 | Translucent | 27-33 | 5.5 | 13 | 400 | 8 | 65 |
| HS -3440 | Translucent | 37-43 | 7.5 | 16 | 350 | 8 | 50 |
| HS -3450 | Translucent | 47-53 | 7.5 | 17 | 300 | 8 | 50 |
| HS -3460 | Translucent | 57-63 | 7.5 | 17 | 250 | 8 | 45 |
| HS -3470 | Translucent | 67-73 | 6.5 | 16 | 200 | 8 | 45 |
| HS -3480 | Translucent | 77-83 | 6 | 16 | 100 | 8 | 40 |

RAJSHILA®