

Standard Silicone Rubber

High glossiness with good rebound resilience, economic and demoulding performance. Suitable for high appearance required molding products.

Grade	Apperance	Hardness(Shore A)	Tensile Strength (Mpa) ≥	Tear Strength (kN/m) ≥	Elongation(%) ≥	Tensile Set (%) ≤	Rebound (%) ≥
HS -3430	Translucent	27-33	5.5	13	400	8	65
HS -3440	Translucent	37-43	7.5	16	350	8	50
HS -3450	Translucent	47-53	7.5	17	300	8	50
HS -3460	Translucent	57-63	7.5	17	250	8	45
HS -3470	Translucent	67-73	6.5	16	200	8	45
HS -3480	Translucent	77-83	6	16	100	8	40



RAJSHILA®