

KOHLNSTOFF® BARONX 45

Speciality Carbon Black

Product Description

BARONX 45 is a low structure high color black its an oxidized carbon black suitable for masstone in a variety of ink applications. The oxidized surface assists dispersion and good flowability in inks. It's easy-to-disperse properties make it easy to process in even at higher loading. This black has a very high blue undertone.

Applications

- Inks including UV cured inks and liquid ink in both water- & solvent-based systems
- Recommended for high gloss solvent flexo inks.
- Suitable for use in articles intended to come in food contact as per Commission Regulation (EU) No 10/2011 and Swiss Ordinance 817.023.21.

Test	ASTM Test Method	Units	Typical Value
BET Surface Area	D-6556	(m ² /gm)	65
Oil Absorption No. (OAN)	D-2414	(cc/100 g)	47
Tint Strength	D-3265	%	100
Sieve Residue # 325	D-1514	ppm	<50
Heating Loss (as packed)	D-1509	%	<3
Volatile Content (@ 950°C)	DIN-53552	%	<3

Packaging

- Product Form: Available in Powder form.
- Regional Availability: Global
- Bag Packaging Options: 20 kg paper bags

Disclaimer:

This information is provided as a convenience and for informational purposes only. No guarantee or warranty as to this information, or any product to which it relates, is given or implied. This information may contain inaccuracies, errors or omissions and Himadri Speciality Chemical Ltd. disclaims all warranties express or implied, including merchantability or fitness for a particular purpose as to (i) such information, (ii) any product or (iii) intellectual property infringement. In no event is Himadri Speciality Chemical Ltd. responsible for, and does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.

KOHLNSTOFF® COLORX 45

Speciality Carbon Black

Product Description

COLORX 45 is a low structure high color black that has been specifically formulated with a high level of color intensity in mind, making it ideal for applications where high gloss and a blue undertone is desired. It's easy-to-disperse properties make it easy to process in even at higher loading. This black has a very high blue undertone.

Application

- Different types of ink application like Flexo Ink, Grave ink, offset, heat set, web set & cold set ink both water based & solvent based system

Test	ASTM Test Method	Units	Typical Range
BET Surface Area	D-6556	(m ² /gm)	62
Oil Absorption No. (OAN)	D-2414	(cc/100 g)	45
Tint Strength	D-3265	%	100
Sieve Residue # 325	D-1514	ppm	<50
Heating Loss (as packed)	D-1509	%	<3

Packaging

- Product Form: Available both in Powder & Bead form.
- Regional Availability: Global
- Bag Packaging Options: 20 kg paper bags

RAJSHILA®

Disclaimer:

This information is provided as a convenience and for informational purposes only. No guarantee or warranty as to this information, or any product to which it relates, is given or implied. This information may contain inaccuracies, errors or omissions and Himadri Speciality Chemical Ltd. disclaims all warranties express or implied, including merchantability or fitness for a particular purpose as to (i) such information, (ii) any product or (iii) intellectual property infringement. In no event is Himadri Speciality Chemical Ltd. responsible for, and does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.